

INVESTIGATION OF THE EFFECT OF LASER RADIATION PARAMETERS ON THE STRUCTURE AND MECHANICAL PROPERTIES OF PARTS OBTAINED BY THE SLM TECHNOLOGY FROM A TITANIUM ALLOY

Agapovichev A.V., Sotov A.V. , Kokareva V.V. , Kyarimov R.R. , Smelov V.G.

Today 3D-printing is a fast developing technology that produces three-dimensional objects directly from digital models through additive process, typically by precipitation and "cured in place" successive layers of polymers, ceramics or metals. Unlike traditional production processes

associated with subtraction, for example, a cutting process or shaping techniques, such as stamping,

bending and molding, AT connects the material layers to create a final product. Originally, this

technology was conceived as a method for producing prototypes, but currently additive manufacturing has improved to the extent that they are increasingly used to obtain the finished

product. Therefore there are high demands on the quality of the synthesized material to details

grown [1].

Selective laser melting technology (SLM) is a fast growing technology that allows to produce

metal parts in a short time. Interest in the technology is growing from year to year. At the moment,

there are several well known works devoted to the study of physical and mechanical properties and

structure of the samples obtained by the SLM. For example, in works [2-3] studies on the impact of

the mode selective laser melting refractory metal powder on the structure of the material are presented.

Despite the fact that the SLM technology has advanced considerably in recent years, its use is

still limited due to the appearance of defects in synthesized parts, for example, such as hollows and

cracks [4]. Also there are questions to the mechanical characteristics of the parts made by the SLM

technology [5]. As is well known, the mechanical characteristics of the material obtained by the

technologies of selective laser melting differ from the mechanical characteristics of the same

material obtained by the traditional technologies.

The quality of the material obtained by the SLM technology is influenced by a large number of parameters, such as the laser emission power, scanning speed, diameter of the laser spot, the

thickness of a sintered layer, structure, the properties of the material used, and many others [2]. The

study of the influence of the SLM technology on the mechanism of structure formation and mechanical characteristics of the synthesized material is, therefore, of considerable interest.

Titanium alloys are widely used for manufacture of parts in aerospace, medical, automobile, chemical and other fields of industry [6, 7]. The main advantages of titanium alloys in

comparison

with structural steels are high unit strength in relation to material density, good rust resistance and

high mechanical characteristics at influence of high temperatures.

VT-6 alloy (analogue ASTM Grade 5 titanium, Ti-6Al-4V) relates to titanium deformable

$\alpha+\beta$ to alloys. High durability such alloys is achieved through use of a heat treatment.

Ultimate

strength of material about 885 MPas at rather high plasticity $\delta=10 \dots 13\%$. With an increase ultimate strength of material up to 1100 MPas leads to receiving enough low values of plasticity, an

order $\delta=4 \dots 6\%$. It is the main reason for the fact that BT6 alloy is in most cases used in not

strengthened state.

VT6 alloy besides the β -stabilizer contains aluminum which is mainly dissolved in a α -phase and strengthens it.

References

1 Smelov V.G., Sotov A. V., Agapovichev A. V. and Tomilina T. M. Selective Laser Melting of

Metal Powder Of Steel 316l, IOP Conf. Series: Materials Science and Engineering Vol. 142,

2 Sufiiarov V. Sh., Popovich A. A., Borisov E. V. and Polozov I. A. Selective laser melting of heatresistant nickel alloy, Tsvetnye Metally. Vol. 2015, Issue 1, 2015, pp 79-84.

3 Grjaznov M. U., Shoshin S. V. and Chuvildeev V. N. Effect of mesostructural hardening of steel 316L during stratified laser alloying, Bulletin of the Nizhny Novgorod University named after N. Lobachevsky. Vol. 5, Issue 1, 2012, pp. 45-50.

4 Baicheng Z., Lucas D., Christian C. The study of the laser parameters and environment variables effect on mechanical properties of high compact parts elaborated by selective laser

melting 316L powder, Materials Science and Engineering: A., Vol. 584, 2013, pp. 21-31.

5 Mohamed A.E. Saleh and Adham E.R. Ti-6Al-4V Helical Spring Manufacturing via SLM: Effect of Geometry on Shear Modulus 2013, Proceedings of the International MultiConference

of Engineers and Computer Scientists, Vol. 2, 2013

6 Sallica-Leva E., Jardini A. and Fogagnolo J. Microstructure and mechanical behavior of porous

Ti-6Al-4V parts obtained by selective laser melting., J. of the Mechanical Behavior of Biomedical Materials., Vol. 26, 2013, pp. 98-108.

7 Banerjee, D. and Williams. Perspectives on Titanium Science and Technology, Acta Materialia.,

Vol. 61, Issue 3, 2013, pp. 844-879.

© Agapovichev A.V., Sotov A.V., Kokareva V.V., Kyarimov R.R., SmelovV.G., 2017